
PROTECPEL AQ

Removable varnish in aqueous phase for all surfaces.



- To protect paint spray booth walls against paint or uarnish stains
- To protect mechanical parts against scratches, scrapes or rust caused by handling or machining operations (bending, stamping...)
- To prepare masks for subsequent painting or electroplating
- To replace paper packaging for the delivery of parts or other objects.

If spray booths or parts are galuanised or not treated, then PROTECPEL AQ should be applied.

Aduantages

- Protects many surfaces
- · Enhances spray booth brightness
- · An eco-friendly product
- · Easy to apply
- Highly flexible: Withstands stamping and folding
- · Good chemical resistance
- Easily removed
- · Withstands high temperatures













Packaging

Our PROTECPEL AQ uarnish is delivered in 5 kg, 10 kg, and 30 kg containers.

Instructions for use

- 1. PROTECPEL AQ AQ can be used in two ways:
 - ° Spray gun: A thick layer of uarnish should be applied. Use a 0.5mm nozzle, the pot pressure must be between 4 and 6 kg/cm and the spray gun pressure between 4 and 6 kg/cm.
 - ° Soaking: Apply as is.

If necessary, apply with a brush to obtain a mask on small surfaces. Raised lettering, embellishments...

2. Air dry. At 20°C, this takes 8 to 10 hours.

Caracteristics

APPEARANCE Thick white opaque liquid

MASS UOLUME at 20°C 1.10 1.12 g/cm3 (in accordance with NF T 60101)

UISCOSITY at 20°C

8-11 Poise EPPRECHT
Uiscometer

FLASH POINT Non flammable

DRY EXTRACT - 3hrs at 105° C 51 - 55 % NF. T 30013

TYPE OF FILM White, flexible film FILM THICKNESS 80 – 100 microns


THINNING AGENT Water

RESISTANCE Not sensitive to organic solvents and water

DRYING TIME 8 hours at 20°C in air









Tel: 00 33 (0) 2 97606833 - Fax: 00 33 (0) 2 97445245



www.profilt.net - contact@profilt.net